


TENSILE STRENGTH TEST RESULT - HOLDON[®] MIDI

Testing machine: SAUTER TVM-N
Pulling speed: 20 mm per Minute

Designation: Holdon[®] MIDI clip-on eyelets. The holding efficiency is tested on 700 g/sqm coated vinyl fabric (Dicoplan), with cord in fold. Video recorded.

Test result: (X) Maximum breaking load: 1125 N



Midi on folded pvc tarp dicoplan w cord in fold

